## TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

## CERTIFICATE OF CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with the manufacturing specifications for this product. This product meets the performance requirements of A-A-56032D TYPE II as it applies to printed circuit board applications, and the requirements of IPC-4781.

... 5001337

S-200W LP Part A	Lot# 002132+	Mfg. Date: 2-13-2- Warranty Ends: 11-13	
PDODEDTY/	TECT METHOD	MANUFACTURING	
PROPERTY VISCOSITY	TEST METHOD  Toki Sangyo RE100U Viscometer  5 rpms @ 25°C	SPECIFICATION After mixing: 130 - 150	RESULT 137 ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	After mixing: Report Only	1.4
FINENESS OF GRIND	TAI-0-0002	17.5 microns maximum	5 microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed U
SCREENABILITY	Visual inspection of coated panel	No surface defects, such as bubbles, pinholes, etc.	Passed
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 2 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C / 30 mins.	No swelling, softening, or blistering	Passed
PENCIL HARDNESS (*)	TAI-0-0020	7H or greater	8 H
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed
(*) - Final This prod	by the Taivo	C (284 <sup>o</sup> F) in a convection ove	n

America Quality Control department and has been granted a warranty extension.

Warranty period ends:

FRM-0-0179 12/13/20

CALLETT

Authorized By: Luis Marquez QC Supervisor Verified, By:

Orc. Supervisor 2/25/20
Title, Date

10/21/15