TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

PSR-4000 GEC50	Lot#1031837	Mfg. Date: 3-18-2-1 Warranty Ends: 9-18-	21	
PROPERTY VISCOSITY	TEST METHOD Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION Before mixing: 250 - 310 ps After mixing: 150 - 180 ps		LT ps ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	Before mixing: 1.1 - 1.5 After mixing: 1.1 - 1.4	1.3	
FINENESS OF GRIND	TAI-0-0002	5 microns maximum	5	microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed	V
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed	Ø
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed	Ø
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed	V
IMAGING	ORC HMW 680GW - 7 kW 300 mJ / cm ² Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi	Report Only (clear on copper)	10	
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 30 sec x 1 cycle Rosin-based flux	No discoloration, peeling, or blistering	Passed	। व
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C / 20 mins.	No swelling, softening, or blistering	Passed	
PENCIL HARDNESS (*)	TAI-0-0020	7H or greater	8 H	•
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed	l U

(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Verified By:

Ve

FRM-0-0146

1/28//09