TAIYO AMERICA, INC.
2675 Antler Drive, Carson City, NV 89701
Phone: (775) 885-9959 Fax: (775) 885-9972

# CERTIFICATE OF ANALYSIS and CONFORMANCE

**This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.**
**This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE and is UL recognized 94V-0 (File #E166421, UL Name: PSR-4000DE).**

**PSR-4000HFX Satin DI** **Lot #** 0022807 **Mfg. Date:** 2-28-20
**Warranty Ends:** 11-28-20

| PROPERTY | TEST METHOD | MANUFACTURING SPECIFICATION | RESULT |
|---|---|---|---|
| VISCOSITY | Toki Sangyo RE100U Viscometer<br>5 rpms @ 25°C | After mixing: 220 - 270 ps | 241 ps |
| THIXOTROPIC INDEX | Toki Sangyo RE100U Viscometer<br>Viscosity ratio: 5 rpm / 50 rpm | After mixing: Report Only | 1.2 |
| FINENESS OF GRIND | TAI-0-0002 | 5 microns maximum | 5 microns |
| VISUAL EXAMINATION | Microscopic examination: | | |
| | 1. 1-mil drawdown of wet film | No bubbles, pits, voids, particles, color differences. | Passed ☑ |
| | 2. Wet film drawdown on grind gauge | No bubbles, pits, voids, particles, color differences. | Passed ☑ |
| SCREENABILITY | Visual inspection of screen printed panel | No surface defects, such as bubbles, pinholes, etc. | Passed ☑ |
| TACK-DRY | Hot air convection oven<br>80°C / 30 minutes | Tack-free to the touch | Passed ☑ |
| IMAGING | ORC HMW 680GW - 7 kW<br>400 mJ / $cm^2$<br>Horizontal Developer - 1% Na2CO3<br>30°C (86°F) / 60 secs., 28 psi | Stouffer 21 step: 10 - 14<br>(clear on copper) | 13 |
| RESISTANCE TO SOLDERING (*) | 260°C (500°F) / 30 sec x 1 cycle<br>Rosin-based flux | No discoloration, peeling, or blistering | Passed ☑ |
| SOLVENT RESISTANCE (*) | Immersion in PM Acetate<br>20°C / 20 mins. | No swelling, softening, or blistering | Passed ☑ |
| PENCIL HARDNESS (*) | TAI-0-0020 | 6H or greater | 8H |
| ADHESION (*) | TAI-0-0021 | 100/100 on copper | Passed ☑ |

**(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven**

**Verified By:**
Q.C. Supervisor 3/2/20
**Name, Title, Date**