TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

Mfg. Date: |2-17-20|Warranty Ends: |2-17-2|Lot # 0121787 **PSR-4000 SW01TA** MANUFACTURING **PROPERTY TEST METHOD SPECIFICATION** RESULT VISCOSITY Toki Sangyo RE100U Viscometer . 169 ps 5 rpms @ 25°C After mixing: 145 - 175 ps THIXOTROPIC INDEX Toki Sangyo RE100U Viscometer 1.2 Viscosity ratio: 5 rpm / 50 rpm After mixing: 1.0 - 1.2 **FINENESS OF GRIND** 5 TAI-0-0002 15 microns maximum microns VISUAL EXAMINATION Microscopic examination: 1. 1-mil drawdown of wet film No bubbles, pits, voids, Passed particles, color differences. 2. Wet film drawdown on **Passed** No bubbles, pits, voids, grind gauge particles, color differences. **SCREENABILITY** Visual inspection of screen Passed No surface defects, printed panel such as bubbles, pinholes, etc. **TACK-DRY** Hot air convection oven Гď Tack-free to the touch Passed ·80°C / 30 minutes **IMAGING** 10 **ORC HMW 680GW - 7 kW** Stouffer 21 step: Report Only 600 mJ / cm² (clear on copper) Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi **RESISTANCE TO** 260°C (500°F) / 10 sec x 3 cycles No discoloration, peeling, Passed **SOLDERING** (*) Rosin-based flux or blistering SOLVENT Immersion in PM Acetate Passed No swelling, softening, **RESISTANCE** (*) 20°C / 20 mins. or blistering 6 H PENCIL HARDNESS (*) TAI-0-0020 5H or greater ADHESION (*) TAI-0-0021 Passed 100/100 on copper

(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven.

Verified By:

Verified By:

Name,

Title,

Date

FRM-0-0222