## TAIYO AMERICA, INC.

## 2675 Antler Drive, Carson City, NV 89701

Phone: (775) 885-9959 Fax: (775) 885-9972

## CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with the manufacturing specifications for this product.

TER-20 K27

Lot# 912123.7

Mfg. Date: |2-|2-|9|Warranty Ends: 6-|2-20|

2	MANUFACTURING		
PROPERTY	TEST METHOD	<b>SPECIFICATION</b>	RESULT
VISCOSITY	Toki Sangyo RE100U Viscometer		
	5 rpms @ 25°C	135 - 165 ps	150 ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	1.10 – 1.50	1.47
FINENESS OF GRIND	TAI-0-0002	, 15 microns maximum	5 microns
VISUAL EXAMINATION	Microscopic examination:		*
x***	1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed
	Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed
SCREENABILITY	Visual inspection of screen Printed panel	No surface defects,	Passed
TACK-DRY	Hot air convection oven 90°C / 30 minutes	Tack-free to the touch	Passed
IMAGING	ORC HMW 680GW 7kW 100 mJ/cm <sup>2</sup>	Stouffer step: Report Only (clear on copper)	Н
	Horizontal Developer – 1% Na2CO3 30°C (86°F) / 60 secs., 20 psi	8 5	
PENCIL HARDNESS	TAI-0-0020	H Minimum	H
ADHESION	TAI-0-0021	100/100 on copper	Passed
STRIPPABILITY	TAI-0-0028	No ink residue	Passed V

Title, Date

FRM-0-0170