TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE and is UL recognized 94V-0 (File #E166421, UL Name: PSR-4000BN).

PSR-4000BN (HV)	Lot#1031217	Mfg. Date: 3-12-3 Warranty Ends: 3-13	21 1-22
PROPERTY VISCOSITY THIXOTROPIC INDEX	TEST METHOD Toki Sangyo RE100U Viscometer 5 rpms @ 25°C Toki Sangyo RE100U Viscometer	MANUFACTURING SPECIFICATION Before mixing: 325 - 375 ps After mixing: 175 - 225 ps	RESULT 353 ps 204 ps
FINENESS OF GRIND	Viscosity ratio: 5 rpm / 50 rpm TAI-0-0002	After mixing: 1.2 - 1.6	1.5 5 microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids,	Passed [
•	2. Wet film drawdown on grind gauge	particles, color differences. No bubbles, pits, voids, particles, color differences.	Passed
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed 🗹
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed 📝
IMAGING	ORC HMW 680GW - 7 kW 500 mJ / cm ² Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi	Stouffer 21 step: 9 - 13 (clear on copper)	1 0
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 3 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed 🕡
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C / 30 mins.	No swelling, softening, or blistering	Passed U
PENCIL HARDNESS (*)	TAI-0-0020	7H or greater	ן דו
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed 📝

(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Verified By:

Q.C. Sufsevisar 3/19/21

Name, Title, Date

FRM-0-0024