

TAIYO AMERICA, INC.
 2675 Antler Drive, Carson City, NV 89701
 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with the manufacturing specifications for this product.

S-200Y NP (USA)

Lot # 1010617

Mfg. Date: 1-06-21

Warranty Ends: 7-06-21

PROPERTY	TEST METHOD	MANUFACTURING SPECIFICATION	<u>RESULT</u>
VISCOSITY	Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	Before mixing: 290 - 350 ps After mixing: Report Only	296 ps 410 ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	Before mixing: 1.4 - 2.2 After mixing: Report Only	2.1 2.7
FINENESS OF GRIND	TAI-0-0002	17.5 microns maximum	5 microns
VISUAL EXAMINATION	Microscopic examination:		
	1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed <input checked="" type="checkbox"/>
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed <input checked="" type="checkbox"/>
SCREENABILITY	Visual inspection of coated panel	No surface defects, such as bubbles, pinholes, etc.	Passed <input checked="" type="checkbox"/>
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 2 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed <input checked="" type="checkbox"/>
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C / 30 mins.	No swelling, softening, or blistering	Passed <input checked="" type="checkbox"/>
PENCIL HARDNESS (*)	TAI-0-0020	7H or greater	8H
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed <input checked="" type="checkbox"/>

(*) - Final cure for these tests was 20 minutes @ 140°C (284°F) in a convection oven

Verified By:

[Signature] P.I.C. SUPERVISOR 1/8/21
 Name, Title, Date